



Technical data polyurea (hardening: 7 days at RT)

	Test norm	Unit	PH
Aspect	optical		black
Density	ISO 1183	g/cm ³	about 1.1
Shore hardness A	ISO 686		40-45
Tensile strength	ISO 527	MPa	1.5-2.5
Elongation at fracture	ISO 527	%	600-650
Tear resistance	DIN 53515	N/mm	13-18
Abrasion	Taber	Mm ³ /100U	3-6

Source: RAMPF GmbH